

**HEAD OFFICE:**

Plot No. – 12, Sector B1, Local Shopping Complex, Vasant Kunj,  
New Delhi - 110 070 (INDIA).  
Tel: 0091-11-26139256 – 265, Fax: 0091-11-26125739  
Web site: [www.jindalpoly.com](http://www.jindalpoly.com)

**TECHNICAL SPECIFICATION SHEET (J-532)**

**DESCRIPTION:** J532 is Transparent, Co extruded standard clear with both side antistatic coated film having smooth surface, good clarity and good handling property

**APPLICATIONS:** Film suitable for high quality lamination and other general-purpose application.

**SALIENT FEATURES:**

- Excellent antistatic property
- Good clarity and Transparency
- High surface gloss
- Excellent Machinability
- Excellent Mechanical Properties
- Excellent Dimensional Stability

**TECHNICAL DATA**

Properties		Test method	Unit	J-532		
PHYSICAL						
Thickness		ASTM D-374	Micron (Gauge)	75 (300)	100 (400)	125 (500)
Yield		JPFTM	m²/kg (in² /lb)	9.5 (6680)	7.1(4990)	5.7 (4000)
OPTICAL						
Haze		ASTM D-1003	%	2.0	2.2	2.5
Total luminous transmittance		ASTM D-1003	%	89	89	89
MECHANICAL						
Tensile strength (Min)	MD	ASTM D-882	Kg/cm² (psi)	1700 (24200)	1700 (24200)	1700 (24200)
	TD	ASTM D-882	Kg/cm² (psi)	1700 (24200)	1700 (24200)	1700 (24200)
Elongation (Min)	MD	ASTM D-882	%	120	120	120
	TD	ASTM D-882	%	100	100	100
Coefficient of friction (Side-A / B) (Max)	St	ASTM D-1894	-	0.50	0.50	0.50
	Dy	ASTM D-1894	-	0.40	0.40	0.40
THERMAL						
Shrinkage (Max) (150°C / 30 min)	MD	ASTM D-1204	%	2.5	2.5	2.5
	TD	ASTM D-1204	%	1.5	1.5	1.5
SURFACE						
Wetting tension (Min)		ASTM D-2578	Dyne / cm	42	42	42
Electrical						
Surface Resistivity		ASTM D-256	Ohm cm	10^11	10^11	10^11

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. JINDAL POLY FILMS LIMITED suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

JPFTM: JINDAL POLY FILMS TEST METHOD, MD: MACHINE DIRECTION, TD: TRANSVERSE DIRECTION

**WORKS:**

28 - KM, Stone, Nashik - Igatpuri Road,  
Village : Mundegaon, Maharashtra  
Phone : + 91 2553 229100, 231002 / 3 / 5  
Fax: + 91 2553 231004

**HEAD OFFICE:**

Plot No. – 12, Sector B1, Local Shopping Complex, Vasant Kunj,  
New Delhi - 110 070 (INDIA).  
Tel: 0091-11-26139256 – 265, Fax: 0091-11-26125739  
Web site: [www.jindalpoly.com](http://www.jindalpoly.com)

**TECHNICAL SPECIFICATION SHEET (J-532)**

**DESCRIPTION:** J532 is Transparent, Co extruded standard clear with both side antistatic coated film having smooth surface, good clarity and good handling property

**APPLICATIONS:** Film suitable for high quality lamination and other general-purpose application.

**SALIENT FEATURES:**

- Excellent antistatic property
- Good clarity and Transparency
- High surface gloss
- Excellent Machinability
- Excellent Mechanical Properties
- Excellent Dimensional Stability

**TECHNICAL DATA**

Properties		Test method	Unit	J-532	
PHYSICAL					
Thickness		ASTM D-374	Micron (Gauge)	175 (700)	250 (1000)
Yield		JPFTM	m²/kg (in² /lb)	4.1 (2880)	2.9 (2040)
OPTICAL					
Haze		ASTM D-1003	%	3.0	4.5
Total luminous transmittance		ASTM D-1003	%	89	89
MECHANICAL					
Tensile strength (Min)	MD	ASTM D-882	Kg/cm² (psi)	1700 (24200)	1600 (22800)
	TD	ASTM D-882	Kg/cm² (psi)	1700 (24200)	1600 (22800)
Elongation (Min)	MD	ASTM D-882	%	120	120
	TD	ASTM D-882	%	100	100
Coefficient of friction (Side-A / B) (Max)	St	ASTM D-1894	-	0.50	0.50
	Dy	ASTM D-1894	-	0.40	0.40
THERMAL					
Shrinkage (Max) (150°C / 30 min)	MD	ASTM D-1204	%	2.5	2.5
	TD	ASTM D-1204	%	1.5	1.5
SURFACE					
Wetting tension (Min)		ASTM D-2578	Dyne / cm	42	42
Electrical					
Surface Resistivity		ASTM D-256	Ohm cm	10^11	10^11

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. JINDAL POLY FILMS LIMITED suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

JPFTM: JINDAL POLY FILMS TEST METHOD, MD: MACHINE DIRECTION, TD: TRANSVERSE DIRECTION

**WORKS:**

28 - KM, Stone, Nashik - Igatpuri Road,  
Village : Mundegaon, Maharashtra  
Phone : + 91 2553 229100, 231002 / 3 / 5  
Fax: + 91 2553 231004