

**HEAD OFFICE:**

Plot No. – 12, Sector B1, Local Shopping Complex, Vasant Kunj,
New Delhi - 110 070 (INDIA).
Tel: 0091-11-26139256 – 265, Fax: 0091-11-26125739
Web site: www.jindalpoly.com

TECHNICAL SPECIFICATION SHEET (J-611)

DESCRIPTION: J611 is white opaque, one side chemically coated, other side plain film having smooth surface, excellent superior gloss, high opacity and good handling property.

APPLICATIONS: Film suitable for Label printing, Photographic printing, coating and other general application.

SALIENT FEATURES:

- High Opacity
- Excellent adhesion to solvent base ink
- High surface gloss
- Excellent Machinability
- Excellent Mechanical Properties
- Excellent Dimensional Stability

			TECHNICAL DATA			
Properties		Test method	Unit	J-611		
PHYSICAL						
Thickness		ASTM D-374	Micron (Gauge)	50 (200)	75 (300)	125 (500)
Yield		JPFTM	m ² /kg (in ² /lb)	14 (9850)	9.4 (6600)	5.6 (3950)
OPTICAL						
Opacity (Min)		CIE Standard	%	90	93	96
Total luminous transmittance		ASTM D-1003	%	20	15	10
MECHANICAL						
Tensile strength (Min)	MD	ASTM D-882	Kg/cm ² (psi)	1400 (19900)	1400 (19900)	1400 (19900)
	TD	ASTM D-882	Kg/cm ² (psi)	1500 (21300)	1500 (21300)	1500 (21300)
Elongation (Min)	MD	ASTM D-882	%	100	100	100
	TD	ASTM D-882	%	80	80	80
Coefficient of friction (Side-A / B) (Max)	St	ASTM D-1894	-	0.35	0.35	0.35
	Dy	ASTM D-1894	-	0.30	0.30	0.30
THERMAL						
Shrinkage (150°C / 30 min) (Max)	MD	ASTM D-1204	%	2.5	2.5	2.5
	TD	ASTM D-1204	%	1.5	1.5	1.5
SURFACE						
Wetting tension (Min)		ASTM D-2578	Dyne / cm	40	40	40
Electrical						
Volume Resistivity		ASTM D-256	Ohm cm	10^16	10^16	10^16

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. JINDAL POLY FILMS LIMITED suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

JPFTM: JINDAL POLY FILMS TEST METHOD, MD: MACHINE DIRECTION, TD: TRANSVERSE DIRECTION

DESCRIPTION: J611 is white opaque, one side chemically coated, other side plain film having smooth surface, excellent superior gloss, high opacity and good handling property.

WORKS:

28 - KM, Stone, Nashik - Igatpuri Road,
Village : Mundegaon, Maharashtra
Phone : + 91 2553 229100, 231002 / 3 / 5
Fax: + 91 2553 231004

**HEAD OFFICE:**

Plot No. – 12, Sector B1, Local Shopping Complex, Vasant Kunj,
New Delhi - 110 070 (INDIA).

Tel: 0091-11-26139256 – 265, Fax: 0091-11-26125739

Web site: www.jindalpoly.com

TECHNICAL SPECIFICATION SHEET (J-611)

APPLICATIONS: Film suitable for Label printing, Photographic printing, coating and other general application.

SALIENT FEATURES:

- High Opacity
- Excellent adhesion to solvent base ink
- High surface gloss
- Excellent Machinability
- Excellent Mechanical Properties
- Excellent Dimensional Stability

TECHNICAL DATA

Properties		Test method	Unit	J-611	
PHYSICAL					
Thickness		ASTM D-374	Micron (Gauge)	175 (700)	250 (1000)
Yield		JPFTM	m ² /kg (in ² /lb)	4.0 (2800)	2.8 (2000)
OPTICAL					
Opacity (Min)		CIE Standard	%	98	99
Total luminous transmittance		ASTM D-1003	%	7	3
MECHANICAL					
Tensile strength (Min)	MD	ASTM D-882	Kg/cm ² (psi)	1400 (19900)	1300 (18500)
	TD	ASTM D-882	Kg/cm ² (psi)	1500 (21300)	1400 (19900)
Elongation (Min)	MD	ASTM D-882	%	100	100
	TD	ASTM D-882	%	80	80
Coefficient of friction (Side-A / B) (Max)	St	ASTM D-1894	-	0.35	0.35
	Dy	ASTM D-1894	-	0.30	0.30
THERMAL					
Shrinkage (Max) (150 ⁰ C / 30 min)	MD	ASTM D-1204	%	2.5	2.5
	TD	ASTM D-1204	%	1.5	1.5
SURFACE					
Wetting tension (Min)		ASTM D-2578	Dyne / cm	40	40
Electrical					
Volume Resistivity		ASTM D-256	Ohm cm	10^16	10^16

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. JINDAL POLY FILMS LIMITED suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

JPFTM: JINDAL POLY FILMS TEST METHOD, MD: MACHINE DIRECTION, TD: TRANSVERSE DIRECTION

WORKS:

28 - KM, Stone, Nashik - Igatpuri Road,
Village : Mundegaon, Maharashtra
Phone : + 91 2553 229100, 231002 / 3 / 5
Fax: + 91 2553 231004